



EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

**EDMS 03-401-1**  
**TECHNICAL SPECIFICATIONS**  
**FOR**  
**SUPPLY OF UNDER GROUND SINGLE CORE**  
**MEDIUM VOLTAGE ARMOURED CABLES 12/20**  
**KV & 18/30 KV**

Issue: Nov.-2021 / Rev- 1

توجد بنود اختيارية ( Option items ) يجب تحديدها بواسطة شركة التوزيع قبل الطرح.



**EEHC DISTRIBUTION MATERIALS SPECIFICATION**

**EDMS 03-401-1**

**Date: 01-12-2021**

**CONTENTS**

<b>1- Scope .....</b>	<b>3</b>
<b>2- Applicable Standards.....</b>	<b>3</b>
<b>3- Environmental Conditions .....</b>	<b>4</b>
<b>4- Service Conditions .....</b>	<b>4</b>
<b>5- System Detail .....</b>	<b>4</b>
<b>6- Design criteria .....</b>	<b>4</b>
<b>7- Construction.....</b>	<b>5</b>
<b>8- Inspection and testing .....</b>	<b>10</b>
<b>9- Identification Of Cable Phases And Marking.....</b>	<b>12</b>
<b>10- Packing .....</b>	<b>12</b>
<b>11- Guarantee .....</b>	<b>13</b>
<b>12- Submittals .....</b>	<b>13</b>
<b>13- Guarantee Tables .....</b>	<b>14</b>



## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

### 1. SCOPE

This specification covers the minimum technical requirements for design, engineering, manufacture, testing, inspection, and construction and medium voltage, 50 Hz , single-core with stranded compact aluminum or copper conductors, extruded semi-conductor screening ,extruded XLPE insulation, extruded semi-insulation screening, copper screen, PVC separation sheath (for armoured cables) , aluminum double tapes armour / non-armour and PVC oversheath cables. The cables shall be used in system with neutral earthed through resistance networks. The cables shall be for underground direct buried.

### 2. APPLICABLE STANDERDS

The cables should be complying with the latest edition of IEC publications unless otherwise specified in this specification. The equipment/material covered in this specification shall comply with the latest edition/amendment of the following codes and standards. Where any provision of this specification differs from those of the standards listed below at table (1) , the provisions of this specification shall apply.

**Table (1)**

S. No.	Standard No.	Description
1.	IEC 60028	International standard of resistance for copper
2.	IEC 60060	High-voltage test techniques
3.	IEC 60228	Conductors of insulated cables.
4.	IEC 60229	Electric cables – Tests on extruded over sheaths with a special protective function
5.	IEC 60230	impulse on cable and their accessories.
6.	IEC 60270	High-Voltage test techniques – Partial discharge measurements
7.	IEC 60287	Electric cables - Calculation of the current rating.
8.	IEC 60502-2	power cables for extruded insulation and their accessories from 6 KV ( $U_m = 7.2$ KV) up to 30 KV( $U_m = 36$ KV).
9.	IEC 60811	Electric and optical fiber cables - Test methods for non-metallic materials.
10. i	IEC 60949	Calculation of thermally permissible short-circuits currents, taking into account non-adiabatic heating effects.



## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

### 3. ENVIRONMENTAL CONDITIONS

The performance of the cables should be guaranteed for following the environmental conditions, any differences in the guaranteed performance should be clearly set out in the offer.

Minimum ambient temperature	: -5°C.
Maximum ambient temperature	: 45°C (50 °c option).
Maximum relative humidity	: 95%
Maximum altitude	: 1000 m.

### 4. SERVICE CONDITIONS

- The sunlight is very intense and the temperature of exposed 70°C.
- The maximum solar radiation intensity on a horizontal surface is 1000 w/m<sup>2</sup>.
- Severe surface contamination from salt, dust, heavy industrial pollution, sandstorms, fine dust often carried in suspension in the atmosphere even on calm days, can be expected.
- Ground temperature can reach 35°C.
- cables should be suitable for direct burial on the following conditions: -

### 5. SYSTEM DETAILS :

Frequency	50 HZ
Nominal voltage	11 / 22 KV
Highest voltage	12 /24 KV

### 6. DESIGN CRITERIA:

#### 1- The cables shall be designed for the following environmental conditions:

- Occasional sand storms.
- Salty air.
- Soil conditions vary from dry sandy to wet silt or clay.
- In some areas the soil is alkaline in others it is acidic or salty.(optional according to ...EDC requirements)

#### 2- The design and construction of cables shall secure the followings:

- Maximum electric strength.
- Maximum mechanical strength.
- Maximum insulation resistance.



## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

- d. Maximum flexibility i.e. minimum bending radius.
- e. Maximum thermal conductivity i.e. maximum heat dissipation.
- f. Minimum thermal expansion and contraction due to overloads and short-circuits i.e. maximum resistance to voids formation i.e. minimum partial discharges.
- g. Minimum capacitance and charging current.
- h. Minimum dielectric losses.

**3- The maximum cables conductor temp. shall be rated for 90oC continuous temperature and 130oC maximum emergency temperature and 250 °C short-circuit temperature.**

### 7. CONSTRUCTION :

#### a- CONDUCTORS: -

The cables shall have stranded compacted circular plain aluminum/ uncoated annealed copper conductors of class 2, The resistance of each conductor at 20 °C shall not exceed the value specified in the latest- relevant applicable IEC 60228 standards.

**The number of wires in the stranded conductors shall be as follow:**

No.	Cable conductor C.S.A mm <sup>2</sup>	Number of wires in the conductor	Max. DC resistance at 20°C (Ω/Km) AL	Max. DC resistance at 20°C (Ω/Km) CU
1	35	7	0.868	0.524
2	50	19	0.641	0.387
3	70	19	0.443	0.268
4	95	19	0.320	0.193
5	120	37	0.253	0.153
6	150	37	0.206	0.124
7	185	37	0.164	0.0991
8	240	61	0.125	0.0754
9	300	61	0.1	0.0601
10	400	61	0.0778	0.047
11	500	61	0.0605	0.0366
12	630	61	0.0469	0.0283
13	800	61	0.0367	0.0221
14	1000	61/91/ milican	0.0291	0.0176



## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

### b- CONDUCTOR SCREENING:

Each conductor shall be covered with an extruded non-metallic, semi-conducting compound layer. The screening layer shall be tightly to the conductor but shall be firmly bonded. The screening layer shall bond thoroughly to the insulation but shall be distinguished from it by its different colour. The minimum thickness of the screening layer, for all size of cables 12/20 KV shall be not less than 0.6 mm and 0.8 mm for cables 18/30 KV.

### c- INSULATION:-

Each conductor shall have an ozone-resistant insulation of cross-linked polyethylene (XLPE) extruded on the conductor screening. The nominal thickness of insulation shall be 5.5 mm and 8 mm for 12/20 KV and 18/30 KV cables respectively. The minimum thickness, at any point, of the insulation shall be not less than 4.85 mm and 7.1 mm for 12/20 KV and 18/30 KV cables respectively.

The minimum average insulation thickness measured during inspection shall be not less than the nominal value.

Requirements for the insulation

\* For each piece of core, the smallest value measured shall not fall below 90 % of the nominal value by more than 0.1 mm, i.e.  $t_{\min} \geq 0.9 t_n - 0.1$

and additionally:  $(t_{\max} - t_{\min}) / t_{\max} \leq 0.15$

Where:

$t_{\max}$ : is the maximum thickness (in millimeters)

$t_{\min}$ : is the minimum thickness (in millimeters)

$t_n$ : is the nominal thickness (in millimeters)

**NOTE:**  $t_{\max}$  and  $t_{\min}$  are measured at the same cross-section.

### d- INSULATION SCREENING:

A non-metallic, semi-conducting compound layer, of different colour than that of the insulation, shall be extruded on the insulation of each core. The insulation screening layer

## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

shall be firmly bonded to the insulation and removable without damaging or scratching the conductor insulation or leaving traces over it during splicing or terminating the cables.

The minimum thickness of the semi-conducting layer shall be not less than 0.8 mm for all size of cables 12/20 KV and 1 mm for cables 18/30 KV.

### e- COPPER SCREEN:

Insulation screening, shall be flat copper tapes or wires or combination of them copper tape shall be applied helically and overlapped. The number of copper tapes or wires and their percentage overlap, shall be selected in such a way to obtain the specified effective cross-sectional area of copper screen of cable. The effective cross-sectional area of copper screen of cable shall be not less than the following:

No.	Number of cores x C.S.A of cable conductor (mm <sup>2</sup> )	Effective C.S.A of copper Screen (mm <sup>2</sup> )/1ph
1	1x35 up to 1x120	16
2	1x150 up to 1x240	25
3	1x300	30
4	≥1x400	35

The effective cross-sectional area of copper screen of cable (A) shall be calculated by the following formula:

**For flat copper tapes, helically applied and overlapped:**

$$A = A_{\text{tape}} + A_{\text{wires}}$$

$$A_{\text{tape}} = \pi D_m t \sqrt{\frac{100}{2(100 - L\%)}}$$

**Where:**

t : Thickness of tape (mm).

d<sub>m</sub>: Diameter of semi-conducting insulation screening (mm) + 2t (mm).

L% : Overlap of copper tape, percent.



## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

### For wires:

$$A_{wires} = \pi d^2 N/4$$

Where:

d : diameter of wire

N: number of wires

### f- SEPARATION SHEATH ( INNER COVERING) IN CASE OF ARMOUR:

The 1-cores cables shall be also inner covered with impervious and non-conducting extruded material in case of armoured cables.

The nominal thickness of the separation sheath shall be calculated by the following Formula:

( $T_s = 0.02 D_u + 0.6$  mm). Where  $D_u$  is the fictitious diameter under this over-sheath in mm.

**The thickness of the separation sheath shall be as follow:**

Number of cores x C.S.A of conductor mm <sup>2</sup>	Nominal (Average) thickness of separation sheath mm	
	12/20 KV	18/30 KV
	AL/CU	AL/CU
1x35	1.3	—
1x50	1.3	1.3
1x70	1.3	1.3
1x95	1.3	1.3
1x120	1.3	1.4
1x150	1.3	1.4
1x185	1.3	1.4
1x240	1.4	1.5
1x300	1.5	1.5
1x400	1.5	1.6
1x500	1.5	1.6
1x630	1.6	1.7
1x800	1.7	1.8
1X1000	1.8	1.9

The measured smallest thickness of the PVC separation sheath, at any point, shall not fall below 80% of the specified nominal value by more than 0.2 mm.





## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

### g- METALLIC ARMOUR:

The single cables shall be armoured by aluminum double-tapes. The armour shall be applied helically in two layers so that the outer tape is approximately central over the gap of the inner tape. The gap between adjacent turns of each tape shall not exceed 50% of the tape width. The armour tape nominal thickness shall be 0.5 mm.

The thickness of the armour shall not fall below the specified nominal value by more than 10% during inspection of the cable.

### h- OVERSHEATH:

The cables shall have impervious extruded PVC oversheath. The oversheath shall be suitable for exposure to sun rays and soil condition in Egypt (see design criteria). The nominal thickness of the oversheath shall be calculated by the following formula:

$$t_s = 0.035 D + 1.0 \text{ mm}$$

where **D** : is the fictitious diameter under the oversheath .

The thickness of the oversheath shall be not less than the following values:

Number of cores x C.S.A of conductor (mm <sup>2</sup> )	Nominal (Average) thickness of oversheath (mm)			
	12/20 KV		18/30 KV	
	Armour	non-armour	Armour	non-armour
1x35	2.1	1.8	—	—
1x50	2.3	1.9	2.4	2.1
1x70	2.3	1.9	2.5	2.1
1x95	2.4	2.0	2.5	2.2
1x120	2.4	2.1	2.6	2.2
1x150	2.5	2.1	2.7	2.3
1x185	2.5	2.2	2.7	2.3
1x240	2.6	2.2	2.8	2.4
1x300	2.7	2.3	2.8	2.5
1x400	2.8	2.4	3	2.6
1x500	2.9	2.5	3.1	2.7
1x630	3	2.7	3.2	2.9
1x800	3.1	2.9	3.3	3
1X1000	3.3	3	3.5	3.2

The measured smallest thickness of the PVC oversheath, at any point, shall not fall below 80 % of the specified nominal value by more than 0.2 mm.



## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

### 8. INSPECTION AND TESTING :-

- Electricity Distribution Company (...EDC) reserves its right to carry out inspection during fabrication stages and witness the testing of the cables.
- Unless otherwise specified or approved in writing by (...EDC), the cables should be subjected to type, routine and special tests in accordance with all relevant applicable IEC standards.
- Testing procedures and rejection of cables should be in accordance with all relevant applicable IEC standards.
- All tests should be carried out by the manufacturer and at his expense and under control and supervision of ( ...EDC) inspection engineers.
- The type, routine and special tests certificates should be delivered to (...EDC).
- Attendance of (...EDC) representatives during fabrication stages and testing shall not relieve the manufacturer of his full responsibility for furnishing the cables in accordance with the requirements of this specification and shall not give him the right to invalidate any claim that (...EDC) may make because of defective or unsatisfactory material or faulty workmanship.

#### 8.1.Type tests:

Medium voltage single core cable shall be tested in accordance to the latest relevant standards IEC 60502-2 and this specification. It shall be the responsibility of the manufacture to perform or to have performed all the tests specified. All type tests had to be performed by accredited laboratories. The type test reports to be submitted shall include as the following:

##### a) Electrical tests on completed cable:

- 1- Bending test, followed by partial discharge test.
- 2- Tan  $\delta$  measurements
- 3- Heating cycle test followed by partial discharge test.
- 4- Impulse test followed by a voltage test.
- 5- Voltage test for 4 hours
- 6- Resistivity of semi-conducting screen.

##### b) Non-Electrical tests on cable components:

1. Measurement of thickness of insulation.



## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

2. Measurement of thickness of non-metal sheaths.
3. Test for determining mechanical properties of insulation before and after ageing.
4. Test for determining mechanical properties of non-metal sheaths before and after ageing.
5. Additional ageing test on pieces of completed cables
6. Loss of mass test on PVC sheath.
7. Hot set test for XLPE insulation.
8. Shrinkage test for XLPE insulation.
9. Test for resistance of PVC insulation and sheath to cracking (heat shock test).

### 8.2. Routine tests:

#### a) Measurement of the electrical dc resistance of conductors.

The dc resistance of conductor at 20°C shall not exceed the appropriate maximum value specified in IEC 60228.

#### b) Partial discharge test

The partial discharge test shall be carried out in accordance with IEC60885-3 except that the sensitivity as defined in IEC 60885-3 shall be 10 pC or better. The voltage being applied between conductor and the screen.

The test voltage shall be raised gradually to and held  $2U_0$  for ten seconds and then slowly reduced to  $1.73 U_0$

There shall be no detectable discharge exceeding the declared sensitivity from the test object at  $1.73 U_0$

#### c) Voltage test

The voltage shall be applied for 5 minutes between the conductor and the metal screen.

The power frequency test voltage shall be  $3.5 U_0$  as shown in below table:

Rated voltage $U_0$ (kV)	12	18
Test voltage (kV)	42	63

**No breakdown of the insulation shall occur**



## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

### 9. IDENTIFICATION OF CABLE AND MARKING:

The cable over sheath shall be marked throughout its length with the following items:

- 1- Rated Voltage.
- 2- Size (number of cores x C.S.A. of conductor mm<sup>2</sup>).
- 3- Material of conductors.
- 4- Manufacturer's name.
- 5- Year of manufacture.
- 6- Customer name (...EDC).
- 7- Cable length.

Distances between marking shall not exceed one meter and each mark shall serially indicate the remaining length of the cable.

### 10. PACKING:

- 1- The cable length on each reel shall be as long as possible to minimize the number of joints and shall be as follows:

Cable size (mm <sup>2</sup> )	Cable length on reel (m) ±5%			
	12/20 KV		18/30 KV	
	AL	CU	AL	CU
1x35	1000	1000	---	---
1x50	1000	1000	1000	1000
1x70	1000	1000	1000	1000
1x95	1000	1000	1000	1000
1x120	1000	1000	1000	1000
1x150	1000	1000	1000	1000
1x185	1000	1000	1000	1000
1x240	1000	800	1000	800
1x300	1000	800	1000	800
1x400	800	600	800	600
1x500	800	600	800	600
1x630	800	500	600	500
1x800	600	500	500	400
1X1000	500	400	500	400



## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

- 2- All cable ends shall be firmly secured to the reel and shall be covered by heat-shrinkable end caps.
- 3- The cable reels shall be covered with wooden slabs of suitable thickness or with (الواح البولي إثيلين - الواح البولي بروبيلين).
- 4- All cables shall be supplied on reels whose size not to exceed 2.7 m diameter and 1.7 m width including protrusion bolts length. The reels may be returnable as per agreement between the tender and ...EDC.
- 5- On each reel, the following data shall be printed on both sides:
  - \* For (...EDC): ARAB REPUBLIC OF EGYPT.
  - \* MEDIUM VOLTAGE POWER CABLES.
  - \* MANUFACTURED BY :
  - \* VOLTAGE CLASS: KV
  - \* NUMBER OF CORES x CROSS-SECTION : mm<sup>2</sup>
  - \* MATERIAL OF CONDUCTORS: AL/CU
  - \* TYPE OF INSULATION : XLPE
  - \* LENGTH OF CABLE: M
  - \* GROSS WEIGHT: KGS
  - \* NET WEIGHT: KGS
  - \* REEL NO / Date of manufacture :

### 11. GUARANTEE:

- The supplier shall guarantee the cables against all defects arising out of faulty design or manufacturing defects or defective material for a period of 18 months from the date of delivery or 12 months from date of installation .

### 12. SUBMITALLS :

The tenderer shall submit with his offer single copies of detail drawings of cable construction, instructions illustrating and explaining the design criteria and design bases, reference standards applied to the cables and instructions for erection, operation, quality control procedure and maintenance. The tenderer shall fill in thoroughly in type-writing the attached guarantee data for the offered cables.



## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

### 13.GUARANTEE TABLE

<b><u>A - TECHNICAL PARTICULARS:</u></b>		
- Manufacturer's name		
- Standards applied to cable		
- Nominal voltage	KV	
- Shape of conductors		
- Diameter of strands	mm	
- Number of conductor strands		
- Overall diameter of conductor	mm	
- Cross-sectional area of conductor	mm <sup>2</sup>	
- Material of conductors		
- Material of conductor screening		
- Thickness of conductor screening		
* Nominal value	mm	
* Minimum value	mm	
- Conductor insulation	XLPE	
- Thickness of conductor insulation		
* Nominal value	mm	
* Minimum value	mm	
- Material of insulation screening		
- Thickness of insulation screening		
* Nominal value	mm	
* Minimum value	mm	
- Material of screen tape	Copper	
- Thickness of tape	mm	
- Width of tape	mm	
- Percentage overlap of tape	%	
- Number of tapes		
- No. of copper wires screen / diameter of wire		
- Effective cross-sectional area of screen per phase	mm <sup>2</sup>	
- Material of separation sheath		
- Minimum thickness of separation sheath	mm	
- Material of armour tapes/wires		
- Nominal thickness of armour tape	mm	
- Minimum thickness of armour tape	mm	
- Number of armour tapes		



## EEHC DISTRIBUTION MATERIALS SPECIFICATION

EDMS 03-401-1

Date: 01-12-2021

- Number of armour wires / diameter	mm	
- Material of oversheath		
- Thickness of oversheath		
* Nominal value	mm	
* Minimum value	mm	
- Overall cable diameter	mm	
- Minimum bending radius of cable	mm	
- Cable weight per meter		
* Aluminum	g	
* Copper sheath	g	
* Finished cable	g	
- Length of cable per drum	m	
- Diameter of drum	m	
- Width of drum	m	
- Gross weight of charged drum	kg	
<b><u>B- PERFORMANCE:</u></b>		
- Power frequency withstand test voltage	kV	
- Duration of power frequency withstand voltage	minutes	
- 1.2/50 $\mu$ s impulse-withstand test voltage	kV	
- Insulation resistance measured by 5000V M.ohmmeter for 10 meters of cable at 20°C	M.ohm	
- Thermal conductivity of finished cable	w/cm°C	
- Partial discharge of cable at 1.73 U <sub>0</sub>	Pc	
- Maximum equivalent star capacitance / km	$\mu$ f	
- Maximum loss angle (tan $\delta$ ) at U <sub>0</sub> and 20°C		
- Maximum D.C. resistance of conductor per km of cable at 20°C	Ohm/km	
- Maximum A.C. resistance of conductor per km of cable at 90°C	Ohm/km	
- Inductance per core per km of cable	mH	
- Equivalent star reactance per km of cable 50 c/s	Ohm/km	
- Impedance per km of cable at 90°C and 50 c/s	Ohm/km	
- Maximum continuous current rating		
* In air 45°C	Amps	
* In ground 30°C	Amps	
- Maximum one second short circuit current capacity of:		



**EEHC DISTRIBUTION MATERIALS SPECIFICATION**

**EDMS 03-401-1**

**Date: 01-12-2021**

* Conductor	KA	
* Screen for one phase	KA	
- Maximum cable temperature		
* Continuous	°C	
* Emergency	°C	
* Short circuit	°C	

I / we certify that the above-mentioned data are guaranteed for the offered cable

Signature:

Date: